

Sinpolene MBW3282/AO

- Low Density Polyethylene

Friday, June 30, 2017

General Information

Product Description

Sinpolene White MBW3281/AO is a polyethylene-based pure white masterbatch designed specifically for use in tubular film blowing, blow moulding and extrusion of polyolefins. With its extremely high pigment loading, Sinpolene White MBW3281/AO offers high colouring value with excellent quality and performance.

The blue undertone of this masterbatch is attributed by specially selected high performance, fine crystal size rutile titanium dioxide.

Sinpolene White MBW3281/AO is delivered as free flowing pellets for processing convenience.

CHARACTERISTICS

- * Easy processing
- * Good dispersion
- * High opacifying power
- * Excellent whiteness

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Filler / Reinforcement	• Titanium Dioxide, 60% Filler by Weight
Features	• General Purpose
Uses	• Film
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Film Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.73		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0 to 8.0	g/10 min	ASTM D1238
Moisture Content	< 0.20	%	ASTM D3030

Additional Information

Recommendation: 3 - 10%

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 4/9/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.