

808

## - Rigid Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	<ul> <li>Commercial: Active</li> </ul>				
Availability	Asia Pacific				
Features	High Gloss	High Impact Resistance			
Uses	Conduit	Piping	<ul> <li>Profiles</li> </ul>		
Forms	<ul> <li>Pellets</li> </ul>				
Processing Method	<ul> <li>Extrusion</li> </ul>				

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.41		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength <sup>2</sup> (Yield)	5690	psi	ASTM D638		
Tensile Elongation <sup>2</sup> (Break)	150	%	ASTM D638		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	2.6	ft·lb/in	ASTM D256		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	78		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Vicat Softening Temperature	201	°F	ASTM D1525		
Thermal Stability <sup>3</sup> (374°F)	> 50	min	BS 2782		

## **Notes**

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 1/2/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> 9.8 in/min

<sup>&</sup>lt;sup>3</sup> Congo Red