

- Rigid Polyvinyl Chloride

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Good Impact Resistance • Good Processability
Uses	• Fittings
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	6540	psi	ASTM D638
Tensile Elongation ² (Break)	100	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.3	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	189	°F	ASTM D1525
Thermal Stability ³ (374°F)	> 30	min	BS 2782

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min

³ Congo Red

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 1/2/2013