

- Rigid Polyvinyl Chloride

Thursday, June 29, 2017

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Flame Retardant • Medium Gloss • Medium Impact Resistance
Uses	• Electrical/Electronic Applications • Piping • Profiles
Forms	• Granules
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6680	psi	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.73	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	208	°F	ASTM D1525
Heat Stability - Congo Red (374°F)	30.0	min	BS 2782

Additional Information

Typical temperature profile for SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

- Feeding zone: 160°C
- Compression zone: 160°C~170°C
- Mixing zone: 170°C~180°C
- Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

<p>Teknor Apex Company Corporate Headquarters</p> <p><i>In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)</i></p> <p>505 Central Avenue Pawtucket, Rhode Island 02861 U.S.</p> <p>Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864</p>	<p>Teknor Apex U.K. Ltd.</p> <p>Tat Bank Road Oldbury, West Midlands B69 4NH England</p> <p>Phone: (44) 121-665-2100 Fax: (44) 121-544-5530</p> <p>etpsales@teknorapex.co.uk</p>
---	---

info@teknorapex.com



Revision Date: 4/22/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.