😰 TEKNOR APEX

# Sinvicomp SIZ4809

## - Rigid Polyvinyl Chloride

Thursday, June 29, 2017

### **General Information**

General	
Material Status	Commercial: Active
Availability	Asia Pacific
Uses	Appliance Wire Insulation
RoHS Compliance	RoHS Compliant
Forms	Pellets
Processing Method	Extrusion

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.48		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	2470	psi	IEC 811-1-1	
Tensile Elongation (Break)	250	%	IEC 811-1-1	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	90		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Hot Deformation - @ 120°C for 1 hr	15	%	BS 6746	
Thermal Stability - Congo Red (374°F)	> 1	hr	BS 2782	
Aging	Nominal Value	Unit	Test Method	
Mechanical Properties After Aging in Air Oven, 168 hr <sup>2</sup>			IEC 60811	
Change in Tensile Elongation	20	%		
Change in Tensile Strength	10	%		
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity (73°F)	2.0E+14	ohms∙cm	BS 2782 230A	
Additional Information	Nominal Value	Unit	Test Method	
Loss of Mass - Oven Ageing Condition @ 100 $\pm$ 2°C for 7 days <sup>3</sup>	1.70	mg/cm <sup>2</sup>	IEC 811-3-2	

Typical temperature profile for SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C Compression zone: 160°C~170°C Mixing zone: 170°C~180°C Nozzle/Die Zone: 180°C

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> @ 100 ± 2°C

<sup>3</sup> Method: IEC60811-3-2

上海松鹤塑化料技有限公司 上海松鹤塑化料技有限的一级分销商 TEKNOR APEX特诺尔爱佩斯——现分销商 TEKNOR APEX特诺尔爱佩斯——现分销商 teknorapex.shehsi.com 联系电话:021-58958679

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with selfer's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

## Sinvicomp SIZ4809

### - Rigid Polyvinyl Chloride

#### Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 10/9/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.