

- Rigid Polyvinyl Chloride

Thursday, June 29, 2017

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Medium Impact Resistance
Uses	• Electrical Parts • Fittings
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46		ASTM D792
Congo Red (374°F)	30.0	min	BS 2782
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6540	psi	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.1	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	199	°F	ASTM D1525

Additional Information

Typical temperature profile for SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

- Feeding zone: 160°C
- Mixing zone: 160°C~170°C
- Metering zone: 170°C~180°C
- Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company
Corporate Headquarters
In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
 505 Central Avenue
 Pawtucket, Rhode Island 02861 U.S.
 Phone: 401-725-8000
 Fax: 401-725-8095
 Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.
 Tat Bank Road
 Oldbury, West Midlands B69 4NH England
 Phone: (44) 121-665-2100
 Fax: (44) 121-544-5530
 etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 4/3/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.