

Sinvicomp SZN6028A

- Flexible Polyvinyl Chloride

Thursday, June 29, 2017

General Information

Product Description

"Sinvicomp"SZN 6028A is a wire & cable polyvinylchloride compound available in pellet form. SZN 6028A provides good abrasion and chemical resistance to jacketing of cables.

| General | |
|-----------------|--|
| Material Status | |

Forms

- · Commercial: Active
- · Asia Pacific Availability
- Features · Abrasion Resistant
- Uses · Wire Jacketing
- 5V-90
- Wire Types (AS 3147/3191)
- Pellets Extrusion
- Processing Method

| ASTM | ጼ | ISO | Properti | es 1 |
|----------------------------------|---|-----|----------|------|
| $\Delta \mathbf{v} = \mathbf{v}$ | · | 100 | 1 100011 | 63 |

· Chemical Resistant

| AOTIMATIO | 7 i Toperties | | |
|---------------------------------------------------------------------------|---------------|--------|---------------|
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.30 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 2470 | psi | IEC 60811-1-1 |
| Tensile Elongation (Break) | 350 | % | IEC 60811-1-1 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 75 | | ASTM D2240 |
| Thermal | Nominal Value | Unit | Test Method |
| Hot Deformation - 120°C, 1hr (248°F) | 45 | % | BS 6469 |
| Aging | Nominal Value | Unit | Test Method |
| Mechanical Properties After Aging in Air Oven, 239°F, 504 hr ² | | | AS 3147/3191 |
| Change in Tensile Elongation | 30 | % | |
| Change in Tensile Strength | 10 | % | |
| Additional Information | Nominal Value | Unit | Test Method |
| Loss of Mass - 115±2°C, 5days ³ (239°F) | 1.20 | mg/cm² | BS 2782 |

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C

Compression zone: 160°C~170°C Mixing zone: 170°C~180°C Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 115±2°C

³ 115±2°C, 5days, BS2782:1970

上海松節進化科技有限公司 上海松節進化科技有限公司 TEKNOR APEX 特度尔爱顺斯 021-58058519 teknorapex.shshsj.com 联系电距: 021-58058519

Sinvicomp SZN6028A

- Flexible Polyvinyl Chloride

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 10/9/2014