

Sarlink® TPV 2940DN-1

Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, June 29, 2017

General Information

Product Description

Sarlink TPV 2940DN-1 is a high performance thermoplastic vulcanizate used in automotive and industrial applications. Sarlink TPV 2940DN-1 is a high hardness, medium density, RoHS compliant grade suitable for extrusion processing.

Seneral			
Material Status	Commercial: Active		
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America
Features	Abrasion Resistant Good Heat Resistance	High Melt Strength High Scratch Resistance	Low Flow Lubricated
Uses	High Hardness Expansion Joint	Light StabilizedGrommets	Medium Density
	GasketsGlazing	PlugsTubing	Weatherstripping
RoHS Compliance	 RoHS Compliant 		
Appearance	 Opaque 		
Forms	• Pellets		
Processing Method	Extrusion		

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.980		ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.80	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (100% Strain)	985	psi	ISO 527-2	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	1930	psi	ASTM D412	
Tensile Elongation (Break)	710	%	ASTM D412	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D, 5 sec)	42		ASTM D2240	
Additional Information				

Hardness, Shore D, Instant = 48 **Legal Statement**

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information		
Extrusion	Nominal Value Unit	
Cylinder Zone 1 Temp.	\$30 to 400 WE	
Cylinder Zone 2 Temp.	240 to 410 10 F	
Cylinder Zone 3 Temp.	TEKNOR 15 15 15 15 15 15 15 15 15 15 15 15 15	
Cylinder Zone 4 Temp.	teknoons 360 to 430 °F	
Cylinder Zone 5 Temp.	360 to 430 °F	
Die Temperature	374 to 440 °F	

Revision Date: 4/13/2017

Sarlink® TPV 2940DN-1

Teknor Apex Company - Thermoplastic Vulcanizate

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S. Phone: 401-725-8000

Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 4/13/2017