

Telcar® TL-2540F

Teknor Apex Company - Thermoplastic Elastomer

Thursday, June 29, 2017

General Information

Product Description

Telcar TL-2540F is a general purpose thermoplastic elastomer designed for a variety of industrial applications. Telcar TL-2540F is a high density, medium hardness grade suitable for extrusion and injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Filled • General Purpose • Good Colorability	• High Density • High Flow • High Specific Gravity	• Medium Hardness • Oil Extended
Uses	• General Purpose • Grommets	• Industrial Applications • Industrial Parts	• Rubber Replacement
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	650	psi	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412
Tear Strength			ASTM D624
Across Flow	99.0	lbf/in	
Flow	91.0	lbf/in	
Compression Set			ASTM D395
73°F, 22 hr	17	%	
158°F, 22 hr	41	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	47		
Shore A, 15 sec	42		

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used for medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F

Revision Date: 6/1/2016

Telcar® TL-2540F

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	350 to 390	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.