

Sarlink® TPV X5735B

Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, June 29, 2017

General Information

Product Description

The Sarlink TPV 5700B series are highly engineered extrusion-grade thermoplastic vulcanizates with outstanding UV stability designed for demanding automotive interior and exterior sealing applications, including glass run channels, waistbelts, weather strips, seals and other profiles. Sarlink TPV X5735B is a low hardness, low density, high performance grade with low fogging and excellent color retention and elastic properties.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Processability • Low Density	• Low Hardness • Low Specific Gravity • Resilient	• UV Resistant
Uses	• Automotive Applications	• Automotive Exterior Parts	• Rubber Replacement
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• CHRYSLER MS-AR-100 IGV Color: Black • FORD Unspecified Color: Black	• GM GMN3927 Color: Black • GM GMW15812P-TPV (EPDM+PP) Type 2 Color: Black	• VAG VW82034 Color: Black • VAG VW91101 Color: Black
Appearance	• Black		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930		ASTM D792
Density	0.930	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	116	psi	
Flow : 100% Strain	247	psi	
Tensile Stress			ISO 37
Across Flow : 100% Strain	116	psi	
Flow : 100% Strain	247	psi	
Tensile Strength			ASTM D412
Across Flow : Break	479	psi	
Flow : Break	377	psi	
Tensile Stress			ISO 37
Across Flow : Break	479	psi	
Flow : Break	377	psi	
Tensile Elongation			ASTM D412
Across Flow : Break	530	%	
Flow : Break	210	%	
Tensile Elongation			ISO 37
Across Flow : Break	530	%	
Flow : Break	210	%	
Tear Strength - Across Flow	57.0	lb/in	ASTM D624
Tear Strength - Across Flow ²	57	lb/in	ISO 34-1
Compression Set			ASTM D395
73°F, 22 hr	12	%	
158°F, 22 hr	23	%	
257°F, 70 hr	42	%	

上海松翰塑化科技有限公司
 TEKNOR APEX 一级分销商
 teknorapex.shshj.com 联系电话: 021-58958519

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV X5735B

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Compression Set			ISO 815
73°F, 22 hr	12	%	
158°F, 22 hr	23	%	
257°F, 70 hr	42	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	34		
Shore A, 5 sec, Injection Molded	36		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	34		
Shore A, 5 sec, Injection Molded	36		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
275°F, 1000 hr	-5.0	%	
100% Strain, 275°F, 1000 hr	4.0	%	
302°F, 168 hr	2.0	%	
100% Strain, 302°F, 168 hr	8.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
275°F, 1000 hr	-5.0	%	
100% Strain 275°F, 1000 hr	4.0	%	
302°F, 168 hr	2.0	%	
100% Strain 302°F, 168 hr	8.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
275°F, 1000 hr	15	%	
302°F, 168 hr	12	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
275°F, 1000 hr	15	%	
302°F, 168 hr	12	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 275°F, 1000 hr	0.0		
Shore A, 302°F, 168 hr	1.0		
Change in Shore Hardness in Air			ISO 188
Shore A, 275°F, 1000 hr	0.0		
Shore A, 302°F, 168 hr	1.0		
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	110	%	ASTM D471
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	110	%	ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
392°F	210	Pa·s	ISO 11443
392°F	210	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV X5735B

Teknor Apex Company - Thermoplastic Vulcanizate

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.