

APEX® 1526-S Black 91

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Uses	Automotive Interior Parts				
Appearance	Opaque				
Forms	• Pellets				
Processing Method	Injection Molding				

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.30		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	1600	psi	ASTM D638		
Tensile Elongation (Break)	330	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240		
A 1 11/1 1 1 6 //					

Additional Information

ACR @ 375F, 25/1 Die 20 PSI = 20 Extrusion Time, Seconds

Temperature Rating = 80 C

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013