

APEX® 84128

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Uses	 Wire & Cable Applications 				
RoHS Compliance	RoHS Compliant				
Appearance	Opaque				
Forms	Pellets				

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.38		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	2550	psi	ASTM D638		
Tensile Elongation (Break)	300	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	89		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	176	°F	ASTM D794		
Brittleness Temperature	-5.80	°F	ASTM D746		
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity (122°F)	5.8E+13	ohms·cm	ASTM D257		
Dielectric Constant			ASTM D150		
1 kHz	4.58				
1 MHz	3.23				
Dissipation Factor			ASTM D150		
1 kHz	0.078				
1 MHz	0.082				
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	30	%	ASTM D2863		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰理化科技有限公司 TEKNOR APEX 特诺尔爱佩斯 teknorapex.shshsj.com 斯泰思语: 021-58958519

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.