

Terraloy™ MB-10000A

Teknor Apex Company - Thermoplastic Starch + LLDPE

Friday, June 30, 2017

General Information

Product Description

Terraloy MB-10000A is a Thermoplastics Starch/LLDPE masterbatch that contains up to 50% of TPS renewable content. Melt index (E) for LLDPE for the masterbatch is 0.9. This compound is for blown film application. Recommended letdown ratio with LLDPE is 1:1.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	• Renewable Resource Content
Uses	• Masterbatch
Forms	• Pellets
Processing Method	• Blown Film

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13		ASTM D792
Melt Mass-Flow Rate (MFR) (210°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Biobased Content	< 50.0		
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	257	°F	ASTM D3418
Additional Information	Nominal Value	Unit	
Let Down Ratio - with LLDPE	1:1		

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.