

## Flexalloy® 9607-96

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information						
General						
Material Status	Commercial: Active					
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America			
Uses	<ul> <li>Wire &amp; Cable Applications</li> </ul>					
RoHS Compliance	RoHS Compliant					
Appearance	Opaque					
Forms	Pellets					

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.42		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	3100	psi	ASTM D638		
Tensile Elongation (Break)	340	%	ASTM D638		
Flexural Modulus	10900	psi	ASTM D790		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore C, 10 sec)	71		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	221	°F	ASTM D794		
Brittleness Temperature	-0.400	°F	ASTM D746		
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity (122°F)	4.2E+12	ohms·cm	ASTM D257		
Dielectric Constant			ASTM D150		
1 kHz	3.99				
1 MHz	2.93				
Dissipation Factor			ASTM D150		
1 kHz	0.071				
1 MHz	5.0E-3				
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	34	%	ASTM D2863		

## **Notes**

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 7/22/2014

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.