

Telcar® TL-2560A

Teknor Apex Company - Thermoplastic Elastomer

Thursday, June 29, 2017

General Information

Product Description

Telcar TL-2560A is a general purpose thermoplastic elastomer designed for a variety of industrial applications. Telcar TL-2560A is a low density, medium hardness grade suitable for both injection molding and extrusion.

General			
Material Status	Commercial: Active		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Features	General PurposeGood ColorabilityHigh Flow	Low DensityLow Specific GravityMedium Hardness	Oil Extended
Uses	General PurposeGrommets	Industrial ApplicationsIndustrial Parts	Rubber Replacement
RoHS Compliance	 RoHS Compliant 		
Appearance	 Natural Color 		
Forms	• Pellets		
Processing Method	 Extrusion 	Injection Molding	

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.890		ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	23	g/10 min	ASTM D1238	
Elastomers	Nominal Value l	Unit	Test Method	
Tensile Strength (Break)	945	psi	ASTM D412	
Tensile Elongation (Break)	770	%	ASTM D412	
Tear Strength			ASTM D624	
Across Flow	140	lbf/in		
Flow	140	lbf/in		
Compression Set			ASTM D395	
73°F, 22 hr	24	%		
158°F, 22 hr	42	%		
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	61		ASTM D2240	
Lamal Otatamant				

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information		
Injection	Nominal Value Unit	
Rear Temperature	340 to 380 °F	
Middle Temperature	TEKNO 350 to 390 °F	
Front Temperature	360 to 400 °F	
Nozzle Temperature	370 to 410 °F	
Processing (Melt) Temp	370 to 410 °F	

Revision Date: 6/1/2016

Telcar® TL-2560A

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	350 to 390	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F
Extrusion Notes		

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 6/1/2016