

Chemlon® 120 G

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

| | General | Information | | |
|-----------------------------------|----------------------------|---------------------------|----------|---------------|
| General | | | | |
| Material Status | Commercial: Active | | | |
| Availability | Asia Pacific | • Europe | | North America |
| Filler / Reinforcement | Glass Fiber, 20% Filler by | / Weight | | |
| Forms | • Pellets | | | |
| Processing Method | Injection Molding | | | |
| | ASTM & IS | O Properties ¹ | | |
| Physical | | Nominal Value | Unit | Test Method |
| Specific Gravity | | 1.26 | | ASTM D792 |
| Molding Shrinkage - Flow | | 3.0E-3 to 6.0E-3 | in/in | ASTM D955 |
| Mechanical | | Nominal Value | Unit | Test Method |
| Tensile Strength | | 18400 | psi | ASTM D638 |
| Tensile Elongation (Yield) | | 2.5 | % | ASTM D638 |
| Tensile Elongation (Break) | | 2.5 | % | ASTM D638 |
| Flexural Modulus | | 798000 | psi | ASTM D790 |
| Flexural Strength | | 27400 | psi | ASTM D790 |
| Impact | | Nominal Value | Unit | Test Method |
| Notched Izod Impact (73°F) | | 1.2 | ft·lb/in | ASTM D256 |
| Thermal | | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | | ASTM D648 |
| 264 psi, Unannealed | | 441 | °F | |
| Melting Temperature | | 495 | °F | DSC |
| Electrical | | Nominal Value | Unit | Test Method |
| Volume Resistivity | | 1.0E+15 | ohms·cm | ASTM D257 |
| Dielectric Strength (0.118 in) | | 460 | V/mil | ASTM D149 |
| Comparative Tracking Index (CTI) | | 600 | V | UL 746 |
| Flammability | | Nominal Value | Unit | Test Method |
| Flame Rating (0.03 in) | | НВ | | UL 94 |
| Oxygen Index | | 25 | % | ASTM D2863 |
| FMVSS Flammability | | PASSES | | FMVSS 302 |
| | Processin | g Information | | |
| Injection | | Nominal Value | Unit | |
| Drying Temperature | | 176 | °F | |
| Suggested Max Moisture | | 0.20 | % | |
| Door Tomporeture | | 40E to 40E | ٥٦ | |

| Processing Information | | | | |
|---|--|--|--|--|
| Injection | Nominal Value Unit | | | |
| Drying Temperature | 176 °F | | | |
| Suggested Max Moisture | 0.20 % | | | |
| Rear Temperature | 465 to 495 °F | | | |
| Middle Temperature | 495 to 520 °F | | | |
| Front Temperature | 505 to 536 °F, | | | |
| Nozzle Temperature | 505 to 540 12 58958519 | | | |
| Processing (Melt) Temp | 505 to 540。全不是 027-5 | | | |
| Notes | LINOR Shehej con | | | |
| ¹ Typical properties: these are not to be construed as specifications. | 495 to 520 °F 505 to 536 °F 505 to 540 学 | | | |

Notes

Revision Date: 7/3/2014

¹ Typical properties: these are not to be construed as specifications.

Chemlon® 120 G

Teknor Apex Company (Chem Polymer) - Polyamide 66

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 7/3/2014