

## Telcar® TL-2503S

## Teknor Anex Company - Thermonlastic Flastomer

reknor Apex Company - Thermopiastic Elastomer			Thursday, June 29, 201			
General Information						
General						
Material Status	Commercial: Active					
Availability	<ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America			
Uses	<ul><li>Consumer Applications</li><li>Flexible Grips</li></ul>	<ul><li>General Purpose</li><li>Handles</li></ul>	<ul><li>Personal Care</li><li>Toys</li></ul>			
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>					
Appearance	Opaque					
Forms	• Pellets					
Processing Method	• Extrusion	Injection Molding				
	ASTM & ISO	Properties <sup>1</sup>				
Physical		Nominal Value Unit	Test Method			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.02		ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10 (	g/10 min	ASTM D1238	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	850	psi	ASTM D412	
Tensile Elongation (Break)	700 9	%	ASTM D412	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 1 sec)	45		ASTM D2240	

Processing Information				
Injection	Nominal Value	Unit		
Rear Temperature	340 to 380	°F		
Middle Temperature	350 to 390	°F		
Front Temperature	360 to 400	°F		
Nozzle Temperature	370 to 410	°F		
Processing (Melt) Temp	370 to 410	°F		
Mold Temperature	77 to 150	°F		
Injection Pressure	200 to 1000	psi		
Injection Rate	Moderate-Fast			
Back Pressure	25.0 to 50.0	psi		
Screw Speed	50 to 100	rpm		
Cushion	0.150 to 1.00	in		
Extrusion	Nominal Value	Unit		
Cylinder Zone 1 Temp.	330 to 370	°F		
Cylinder Zone 2 Temp.	340 to 380			
Cylinder Zone 3 Temp.	350 to 390	°F \\		
Cylinder Zone 5 Temp.	360 to 400	* 地版 / 山南		
Die Temperature	374 to 410	致 2 585/19		
Extrusion Notes	が物理や	*F		
Screw Speed: 30 to 100 rpm	L'APEX R	加联系电阻		
Notes  1 Typical properties: these are not to be construed as specifications.	TEKNOT apex. shshs.	等技有限公開商 特技等關係 021-50058519 所以來用底。021-50058519		
Typical properties, these are not to be constitued as specifications.				

## **Notes**

Revision Date: 9/28/2016

## Telcar® TL-2503S Teknor Apex Company - Thermoplastic Elastomer

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 9/28/2016