🚸 TEKNOR APEX

PVC Film 06-A0370R-80 NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Thursday, June 29, 2017

General Information

General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Features	DEHP Plasticizer	Non-Phthalate Plasticizer	Radiation Sterilizable	
Forms	• Film			

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.23		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2900	psi	ASTM D638	
Tensile Elongation (Break)	330	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	80		ASTM D2240	

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex U.K. Ltd.
In U.S. for Vinute TREE Colorente	Tat Bank Road
In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)	Oldbury, West Midlands B69 4NH England
505 Central Avenue	Phone: (44) 121-665-2100
Pawtucket, Rhode Island 02861 U.S.	Fax: (44) 121-544-5530
Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864	etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.