

## APEX® RM 8002

Teknor Apex Company - Rigid Polyvinyl Chloride

Friday, June 30, 2017

## General Information

## General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Features	• Asia Pacific	• Latin America	
Agency Ratings	• Medium Flow		
Forms	• NSF STD-61		
	• Pellets		

ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	407000	psi	ASTM D638
Tensile Strength (Break)	6730	psi	ASTM D638
Flexural Modulus	401000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.5	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	155	°F	

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex U.K. Ltd.
In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)	Tat Bank Road Oldbury, West Midlands B69 4NH England
505 Central Avenue Pawtucket, Rhode Island 02861 U.S.	Phone: (44) 121-665-2100 Fax: (44) 121-544-5530
Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864	etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.