

# - Linear Low Density Polyethylene

## **General Information**

#### **Product Description**

2401

SINPOLENE MBB2401 is a modified copolymer based black masterbatch designed specifically for use in injection moulding, tubular film blowing, blow moulding and extrusion of polyolefins. SINPOLENE MBB2401 has high pigment loading and thus offers high coloring value with superior quality and performance.

SINPOLENE MBB2401 is delivered as free flowing pellets for processing convenience.

#### **CHARACTERISTICS**

- \* Easy processing
- \* Good dispersion
- \* High jetness
- \* Minimal wear effect on processing equipment

General			
Material Status	Commercial: Active		
Availability	Asia Pacific		
Features	<ul> <li>General Purpose</li> </ul>		
Uses	• Film	• Sheet	
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>		
Forms	<ul> <li>Pellets</li> </ul>		
Processing Method	Blown Film	Sheet Extrusion	

ASTM & ISO Properties 1			
Physical	Nominal Value Unit	Test Method	
Specific Gravity	1.16	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/10.0 kg)	< 30 g/10 min	ASTM D1238	
Carbon Black Content	40 %	ASTM D1603	
Moisture Content	< 0.25 %	ASTM D3030	

#### **Additional Information**

Recommended dosage: 2 - 5%

### **Notes**

#### Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 9/26/2014

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.