

Synres® PP G20 62

Teknor Apex Company - Polypropylene

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Forms	Pellets			

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.02		ASTM D792		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break, 2.00 in)	9350	psi	ASTM D638		
Flexural Modulus	450000	psi	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	16	ft·lb/in	ASTM D256		
Gardner Impact	192	in·lb	ASTM D5420		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D, 10 sec)	70		ASTM D2240		

Additional Information

Heat Deflection, 66 psi = 314 F (ASTM D-648) ASH = 20% (ASTM D-5630)

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013