

## **APEX® 3200-85NT**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information  General				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America	
Additive	<ul> <li>Plasticizer</li> </ul>			
Features	DEHP Plasticizer	Ethylene Oxide Steriliza	able	
Uses	Medical/Healthcare Applications			
Appearance	<ul> <li>Clear/Transparent</li> </ul>			
Forms	• Pellets			
Processing Method	<ul> <li>Injection Molding</li> </ul>			

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.24		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (100% Strain)	1500	psi	ASTM D638	
Tensile Strength (Break)	2550	psi	ASTM D638	
Tensile Elongation (Break)	350	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	85		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-7.60	°F	ASTM D746	

Processing Information		
Injection	Nominal Value Unit	
Processing (Melt) Temp	360 °F	

## **Notes**

## **Teknor Apex Company** Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)

Pawtucket, Rhode Island 02861 U.S.

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Phone: 401-725-8000

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.