

APEX® 3211-85NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

| General Information | | | | | |
|---------------------|---|--|---------------|--|--|
| General | | | | | |
| Material Status | Commercial: Active | | | | |
| Availability | Africa & Middle East Asia Pacific | EuropeLatin America | North America | | |
| Additive | Plasticizer | | | | |
| Features | Ethylene Oxide Sterilizable | Non-DEHP Plasticizer | | | |
| Uses | Medical/Healthcare Applications Toys | | | | |
| Appearance | Natural Color | Opaque | | | |
| Forms | • Pellets | | | | |
| Processing Method | Injection Molding | | | | |

| ASTM & ISO Properties ¹ | | | | |
|--------------------------------------|---------------|------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.34 | | ASTM D792 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (100% Strain) | 1600 | psi | ASTM D638 | |
| Tensile Strength (Break) | 2000 | psi | ASTM D638 | |
| Tensile Elongation (Break) | 260 | % | ASTM D638 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore A, 15 sec) | 85 | | ASTM D2240 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Brittleness Temperature | -9.40 | °F | ASTM D746 | |

| Processing Information | | | |
|------------------------|--------------------|--|--|
| Injection | Nominal Value Unit | | |
| Processing (Melt) Temp | 360 °F | | |

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.