

APEX® 3300-55NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Plasticizer		
Features	• DEHP Plasticizer	• Ethylene Oxide Sterilizable	
Uses	• Food Service Applications	• Medical/Healthcare Applications • Tubing	
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (100% Strain)	520	psi	ASTM D638
Tensile Strength (Break)	1500	psi	ASTM D638
Tensile Elongation (Break)	460	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	55		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-41.8	°F	ASTM D746

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	330	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*

505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.