

Flexalloy® 9400-70

Teknor Apex Company - Polyvinyl Chloride Elastomer

Friday, June 30, 2017

| General Information | | | | | |
|------------------------------------|---|--|---------------|--|--|
| Product Description | | | | | |
| The GM Automotive Specification is | s Suggested, not Approved. | | | | |
| General | | | | | |
| Material Status | Commercial: Active | | | | |
| Availability | Africa & Middle East Asia Pacific | EuropeLatin America | North America | | |
| Features | Ultra High Molecular Weight | | | | |
| Uses | Automotive ApplicationsHose | Profiles Seals | • Tubing | | |
| Automotive Specifications | GM GMP.PVC.062 | | | | |
| Forms | • Pellets | | | | |
| Processing Method | Extrusion | | | | |

| ASTM & ISO Properties 1 | | | | | |
|--------------------------------------|---------------|------|-------------|--|--|
| Physical | Nominal Value | Unit | Test Method | | |
| Specific Gravity | 1.24 | | ASTM D792 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength (Break) | 2200 | psi | ASTM D638 | | |
| Tensile Elongation (Break) | 340 | % | ASTM D638 | | |
| Hardness | Nominal Value | Unit | Test Method | | |
| Durometer Hardness (Shore A, 15 sec) | 70 | | ASTM D2240 | | |
| Thermal | Nominal Value | Unit | Test Method | | |
| Brittleness Temperature | -41.8 | °F | ASTM D746 | | |

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.