

- Rigid Polyvinyl Chloride

Thursday, June 29, 2017

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Medium Impact Resistance
Uses	• Fittings
Agency Ratings	• NSF STD-61
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6960	psi	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.94	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	187	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 5/23/2014