

**- Flexible Polyvinyl Chloride**

Friday, June 30, 2017

**General Information**

**General**

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Radiation Sterilizable
Uses	• Medical/Healthcare Applications
Forms	• Granules
Processing Method	• Extrusion

**ASTM & ISO Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 to 1.24		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield)	> 2130	psi	ASTM D638
Tensile Elongation (Break)	> 250	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	71 to 77		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Heat Stability - Oven (374°F)	> 30.0	min	ASTM D2115-92

**Additional Information**

Typical temperature profile for processing compound is from 135°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process.

- Feeding zone: 135°C
- Compression zone: 145°C~155°C
- Mixing zone: 155°C~175°C
- Nozzle/Die Zone: 165°C~180°C

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 20 in/min

**Teknor Apex Company  
Corporate Headquarters**

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

**Teknor Apex U.K. Ltd.**

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/22/2012

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.