

## APEX® RM 8002A

## Teknor Apex Company - Rigid Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Forms	Pellets				

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.37		ASTM D792		
Molding Shrinkage - Flow	2.8E-3	in/in	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus <sup>2</sup>	430000	psi	ASTM D638		
Tensile Strength <sup>2</sup> (Break)	7100	psi	ASTM D638		
Tensile Elongation (Break)	80	%	ASTM D638		
Flexural Modulus <sup>3</sup>	410000	psi	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact			ASTM D256		
73°F, 0.125 in, Compression Molded	2.8	ft·lb/in			
Drop Impact Resistance <sup>4</sup> (73°F)	2.35	in·lb/mil	ASTM D4226		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D, 10 sec)	81		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load			ASTM D648		
264 psi, Annealed, 0.125 in	156	°F			

## **Notes**

## **Teknor Apex Company** Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864 Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> 0.20 in/min

<sup>&</sup>lt;sup>3</sup> 0.050 in/min

<sup>&</sup>lt;sup>4</sup> Procedure A, TUP