

Sinpolene CP2300 ED3019

- Polypropylene Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East 	Asia Pacific	Latin America		
Additive	Antistatic	 UV Stabilizer 			
Features	Antistatic	 UV Absorbing 			
Uses	 Appliance Components 	Housings			
Forms	• Pellets				
Processing Method	Injection Molding				

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.912		ASTM D792		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238		
Moisture Content	1500	ppm	ASTM D3030		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	3770	psi	ASTM D638		
Tensile Elongation (Break)	780	%	ASTM D638		
Flexural Modulus	138000	psi	ASTM D790		
Flexural Strength	4500	psi	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	12	ft·lb/in	ASTM D256		
Electrical	Nominal Value	Unit	Test Method		
Surface Resistivity	1.0E+9 to 1.0E+10	ohms	IEC 60093		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road

Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 11/24/2015

¹ Typical properties: these are not to be construed as specifications.