

APEX® 77-W002-B

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

| General Information | | | | |
|---------------------|---|--|---------------|--|
| General | | | | |
| Material Status | Commercial: Active | | | |
| Availability | Africa & Middle East Asia Pacific | EuropeLatin America | North America | |
| Features | Fungus Resistant | Low Temperature Flexib | pility | |
| Uses | Military Applications | • Tubing | | |
| Agency Ratings | MIL I-631-D Grade B, Class I, Category I, Form U, Type F MIL I-7444-D Grade B, Class I, Category I | | | |
| Appearance | Clear/Transparent | | | |
| Forms | • Pellets | | | |
| Processing Method | Extrusion | | | |

| ASTM & ISO Properties ¹ | | | | |
|--------------------------------------|---------------|---------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.21 | | ASTM D792 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Break) | 2500 | psi | ASTM D638 | |
| Tensile Elongation (Break) | 430 | % | ASTM D638 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore A, 15 sec) | 80 | | ASTM D2240 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Brittleness Temperature | -58.0 | °F | ASTM D746 | |
| Electrical | Nominal Value | Unit | Test Method | |
| Volume Resistivity | 1.0E+12 | ohms·cm | ASTM D257 | |
| Dielectric Constant (1 kHz) | 5.50 | | ASTM D150 | |
| Flammability | Nominal Value | Unit | Test Method | |
| Oxygen Index | 24 | % | ASTM D2863 | |
| | | | | |

Additional Information

Temperature Rating: 60 °C

Ultimate Elongation Retained, UL 1581, Oven Aged, 7 days, 100°C: 87 % Tensile Strength Retained, UL 1581, Oven Aged, 7 days, 100°C: 108 %

| Processing Information | | |
|------------------------|--------------------|--|
| Extrusion | Nominal Value Unit | |
| Melt Temperature | 355 °F | |

Notes

¹ Typical properties: these are not to be construed as specifications.

上海松節塑化科技有限公司 上海松節塑化科技有限公開商 TEKNOR APEX 特诺尔爱佩斯 TEKNOR APEX 特诺尔爱佩斯 teknorapex.shshsl.com 联系电流: 021-58958519

Revision Date: 12/12/2013

APEX® 77-W002-B

Teknor Apex Company - Flexible Polyvinyl Chloride

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013