

APEX® 162

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Features	Flame Retardant			
Uses	Armored Cable	 Flexible Jacketing 		
Agency Ratings	• MIL C-2194-D	• MIL C-915-C		
RoHS Compliance	 RoHS Compliant 			
Appearance	Opaque			
Forms	• Pellets			
Processing Method	Extrusion			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.41		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2350	psi	ASTM D638	
Tensile Elongation (Break)	360	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	82		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-34.6	°F	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	28	%	ASTM D2863	
Additional Information				

Additional Information

Shipboard cables, armored Temperature Rating: 80 °C

UL Sunlight Resistance Recognition: No

Ultimate Elongation Retained, UL 1581, Oven Aged, 7 days, 113°C: 78 %

Tensile Strength Retained, UL 1581, Oven Aged, 7 days, 113°C: 100 %

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	355 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松前理化科技有限公司 TEKNOR APEX 特诺尔曼佩斯 021-58958519 teknorapex.shshsj.com 斯泰思斯: 021-58958519

Revision Date: 12/12/2013