

APEX® 1850

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Features	High Heat Resistance			
Uses	ConnectorsGrommets	PlugsStrain Reliefs		
Wire Types	 Molded Components 			
RoHS Compliance	 RoHS Compliant 			
Appearance	• Opaque			
Forms	• Pellets			
Processing Method	Injection Molding			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.35		ASTM D792	
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2650	psi	ASTM D638	
Tensile Elongation (Break)	280	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore C, 10 sec)	71		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	1.40	°F	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	28	%	ASTM D2863	
Additional Information				

Additional Information

Temperature Rating: 105 °C

Processing Information			
Injection	Nominal Value Unit		
Processing (Melt) Temp	375 °F		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864 Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松静理化科技有限公司 上海松静理化科技有限公司 TEKNOR APEX 特诺尔爱佩斯 021-58958519 TEKNOR apex.shshsi.com 联系电话: 021-58958519

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.