

APEX® 4103 Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information

Material Status	Commercial: Active		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Uses	ConnectorsGrommets	 Plugs Strain Reliefs	Wire & Cable Applications
Wire Types	 Molded Components 		
Agency Ratings	UL QMFZ2		
RoHS Compliance	 RoHS Compliant 		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.38		ASTM D792		
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	1500	psi	ASTM D638		
Tensile Elongation (Break)	220	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	80		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	140	°F	ASTM D794		
Brittleness Temperature	-14.8	°F	ASTM D746		
RTI Elec			UL 746		
0.03 in	194	°F			
0.12 in	194	°F			
RTI Str			UL 746		
0.03 in	194	°F			
0.12 in	194	°F			
Electrical	Nominal Value	Unit	Test Method		
Comparative Tracking Index (CTI) (0.118 in)	PLC 0		UL 746		
High Amp Arc Ignition (HAI) (0.12 in)	PLC 1		UL 746		
Hot-wire Ignition (HWI) (0.12 in)	PLC 1		UL 746		
Flammability	Nominal Value	Unit	Test Method		
Flame Rating			UL 94		
0.03 in	V-2		(二)		
0.12 in	Vo	科技有限	R 4 销商		
Oxygen Index	125	1%+ 1× HEF	589585ASTM D2863		



Recognized Component, CSA C22.2 No. 0.6, CSA Flammability Classification 0.6V a 0.86 mm

589585ASTM D2863

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

海松

125, 1961 15

大特诺尔爱

同斯

由话

02

Revision Date: 12/12/2013

Processing Information

Injection

Processing (Melt) Temp

Nominal Value Unit

355 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex U.K. Ltd.

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S. Tat Bank Road Oldbury, West Midlands B69 4NH England Phone: (44) 121-665-2100

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

etpsales@teknorapex.co.uk

Fax: (44) 121-544-5530

info@teknorapex.com

Teknor Apex Company

Corporate Headquarters



Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.