

APEX® 4102

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Uses	ConnectorsGrommets	PlugsStrain Reliefs		
Wire Types	Molded Components			
RoHS Compliance	 RoHS Compliant 			
Appearance	• Opaque			
Forms	• Pellets			
Processing Method	Injection Molding			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.31		ASTM D792	
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	1980	psi	ASTM D638	
Tensile Elongation (Break)	400	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	140	°F	ASTM D794	
Brittleness Temperature	-31.0	°F	ASTM D746	
RTI Elec	194	°F	UL 746	
RTI Str	194	°F	UL 746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	27	%	ASTM D2863	
Additional Information				

Additional Information

Strain relief Grommets
Temperature Rating: 60 °C

Processing Information			
Injection	Nominal Value Unit		
Processing (Melt) Temp	345 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.

上海松静理化科技有限公司 上海松静理化科技有限公销商 TEKNOR APEX 特诺尔爱佩斯 TEKNOR APEX 特诺尔爱佩斯 teknorapex.shshsj.com 联系电流: 021–58958519

Revision Date: 12/12/2013

APEX® 4102

Teknor Apex Company - Flexible Polyvinyl Chloride

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013