

Flexalloy® 9600-72

Teknor Apex Company - Polyvinyl Chloride Elastomer

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Features	Flame RetardantHigh Heat Resistance	Low Temperature FlexibilitySunlight Resistant (720 hours)			
Uses	 Cable Jacketing 				
Wire Types	• SEOW • SEW	SJEOWSJEW	• STEOW • STEW		
Agency Ratings	UL Class 11UL Class 12	UL Class 36UL Class 43	• UL QMTT2		
RoHS Compliance	 RoHS Compliant 				
Appearance	• Opaque				
Forms	 Pellets 				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.25		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2100	psi	ASTM D638	
Tensile Elongation (Break)	330	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	221	°F	ASTM D794	
Brittleness Temperature	-63.4	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Constant			ASTM D150	
1 kHz	6.19			
1 MHz	3.91			
Dissipation Factor			ASTM D150	
1 kHz	0.076			
1 MHz	0.11			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	26	%	ASTM D2863	

Notes

¹ Typical properties: these are not to be construed as specifications.

上海松鄉進化科技有限公司 上海松鄉進化科技有限公司 TEKNOR APEX 特诺尔爱佩斯 021-58958519 TEKNOrapex.shshsi.com 联系电流: 021-58958519

Revision Date: 12/12/2013

Flexalloy® 9600-72 Teknor Apex Company - Polyvinyl Chloride Elastomer

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/12/2013