

Chemlon® 66GF6H

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

General Information

Product Description

66GF6H is a 30% glass fibre reinforced, heat stabilised nylon 66 that offers good mechanical performance and endurance at elevated service temperatures, coupled with good surface finish and flow.

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features	• Good Flow • Good Surface Finish • Heat Stabilized
Uses	• High Temperature Applications
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183
Molding Shrinkage ²	0.60 to 1.5	--	%	Internal Method
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	1.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.31E+6	986000	psi	ISO 527-2
Tensile Stress	26100	18100	psi	ISO 527-2
Tensile Strain (Break)	5.0	10	%	ISO 527-2
Flexural Modulus	1.31E+6	740000	psi	ISO 178
Flexural Stress	36300	15200	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength	23	No Break	ft-lb/in ²	ISO 179/1eU
Notched Izod Impact Strength	2.9	9.5	ft-lb/in ²	ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	> 464	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	464	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+13	ohms-cm	IEC 60093
Electric Strength (0.118 in)	410	--	V/mil	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.06 in, Teknor Apex test result	HB			

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	2.0	hr
Rear Temperature	518 to 554	°F

Revision Date: 3/17/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shsh.com 联系电话: 021-58958519

Chemlon® 66GF6H

Teknor Apex Company (Chem Polymer) - Polyamide 66

Injection	Dry Unit
Middle Temperature	518 to 554 °F
Front Temperature	518 to 554 °F
Processing (Melt) Temp	518 to 554 °F
Mold Temperature	176 to 194 °F
Injection Rate	Fast
Back Pressure	Low
Screw Speed	Moderate

Injection Notes

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 3/17/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.