

# Chemlon® A60XT

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

## General Information

### Product Description

A60XT is a modified nylon 66 that offers high impact strength coupled with good rigidity.

### General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• Impact Modifier
Features	• High Impact Resistance      • Impact Modified      • Medium Rigidity
Processing Method	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>	1.6 to 2.3	%	Internal Method
Water Absorption (Equilibrium, 73°F, 50% RH)	2.3	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	305000	psi	ISO 527-2
Tensile Stress	8410	psi	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus	290000	psi	ISO 178
Flexural Stress	9430	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	17	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	365	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	158	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in, Teknor Apex test result)	HB		UL 94
Oxygen Index	22	%	ISO 4589-2

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0	hr
Rear Temperature	518 to 554	°F
Middle Temperature	518 to 554	°F
Front Temperature	518 to 554	°F
Processing (Melt) Temp	518 to 554	°F
Mold Temperature	140 to 176	°F
Injection Rate	Fast	
Back Pressure	Low	



Revision Date: 3/20/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Chemlon® A60XT

## Teknor Apex Company (Chem Polymer) - Polyamide 66

Injection	Nominal Value	Unit
Screw Speed		Moderate

### Injection Notes

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*

505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

#### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司  
TEKNOR APEX 特诺尔爱佩斯 一级分销商  
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 3/20/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.