

## APEX® 90-A471R-75-NT

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Additive	<ul> <li>Plasticizer</li> </ul>				
Features	<ul> <li>DEHP Plasticizer</li> </ul>	<ul> <li>Radiation (Gamma) Resistant</li> </ul>	Radiation Sterilizable		
Uses	Medical/Healthcare Applications    Tubing				
Appearance	<ul> <li>Clear/Transparent</li> </ul>				
Forms	• Pellets				
Processing Method	<ul> <li>Extrusion</li> </ul>				

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value Ur	nit Test Method		
Specific Gravity	1.20	ASTM D792		
Mechanical	Nominal Value Ur	nit Test Method		
Tensile Strength (Break)	2150 ps	si ASTM D638		
Tensile Elongation (Break)	420 %	ASTM D638		
Hardness	Nominal Value Ur	nit Test Method		
Durometer Hardness (Shore A, 15 sec)	75	ASTM D2240		

## **Notes**

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864 Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.