

# **APEX® 1587**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

|                                | General In  | formation                                      |               |
|--------------------------------|---|--|---------------|
| Product Description            |   |  |               |
| Applications include appliance | parts, bumpers, suction cups, and promotio                      | n items.                                       |               |
| General                        |   |  |               |
| Material Status                | Commercial: Active  |  |               |
| Availability                   | <ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul> | North America |
| Features                       | <ul> <li>General Purpose</li> </ul>                             |  |               |
| Uses                           | <ul> <li>Appliance Components</li> </ul>                        | <ul> <li>General Purpose</li> </ul>            |               |
| Appearance                     | <ul> <li>Clear/Transparent</li> </ul>                           |  |               |
| Forms                          | • Pellets   |  |               |
| Processing Method              | <ul> <li>Injection Molding</li> </ul>                           |  |               |

| ASTM & ISO Properties <sup>1</sup>   |               |      |             |  |  |
|--------------------------------------|---------------|------|-------------|--|--|
| Physical                             | Nominal Value | Unit | Test Method |  |  |
| Specific Gravity                     | 1.27          |      | ASTM D792   |  |  |
| Mechanical                           | Nominal Value | Unit | Test Method |  |  |
| Tensile Strength (Break)             | 2800          | psi  | ASTM D638   |  |  |
| Tensile Elongation (Break)           | 300           | %    | ASTM D638   |  |  |
| Hardness                             | Nominal Value | Unit | Test Method |  |  |
| Durometer Hardness (Shore C, 15 sec) | 72            |      | ASTM D2240  |  |  |
| Thermal                              | Nominal Value | Unit | Test Method |  |  |
| Continuous Use Temperature           | 140           | °F   | ASTM D794   |  |  |
| Brittleness Temperature              | 3.20          | °F   | ASTM D746   |  |  |

## Notes

#### Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

### Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.