

APEX® 83-F279-A

Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information				
General				
Material Status	Commercial: Active			
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America	
Features	Low Gloss			
Uses	 Automotive Interior Parts 	• Profiles	• Tubing	
Forms	• Pellets			
Processing Method	 Extrusion 			

ASTM & ISO Properties ¹				
Physical	Nominal Value Unit	Test Method		
Specific Gravity	1.49	ASTM D792		
Mechanical	Nominal Value Unit	Test Method		
Tensile Strength (Break)	2300 psi	ASTM D638		
Tensile Elongation (Break)	280 %	ASTM D638		
Hardness	Nominal Value Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	90	ASTM D2240		

Notes

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.