

## APEX® 74-8126A-37

## Teknor Apex Company - Flexible Polyvinyl Chloride

Friday, June 30, 2017

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Features	Medium Gloss				
Uses	<ul> <li>Automotive Interior Parts</li> </ul>	• Knobs			
Automotive Specifications	GM GMP.PVC.037				
Forms	• Pellets				
Processing Method	Injection Molding				

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.24		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	2550	psi	ASTM D638		
Tensile Elongation (Break)	390	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	82		ASTM D2240		

## **Notes**

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.