

Apparent Viscosity (392°F, 206 sec^-1)

**Legal Statement** 

# Monprene® RG-17250 (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

Friday, June 30, 2017

## **General Information**

### **Product Description**

The Monprene RG-17200 series is a group of high performance thermoplastic elastomers specifically designed for EU injection molded regulated applications including food contact, toys, and children's products. Monprene RG-17250 is a medium density, medium hardness grade that complies with various US FDA and European regulations and directives for food contact and toy safety and is suitable for injection molding. Please contact Teknor Apex for a regulatory compliance letter.

General			
Material Status	Preliminary Data		
Availability	<ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America
Features	<ul><li>Filled</li><li>Food Contact Acceptable</li><li>Good Adhesion</li></ul>	<ul><li>Good Colorability</li><li>Good Processability</li><li>Lubricated</li></ul>	<ul><li> Medium Density</li><li> Medium Hardness</li></ul>
Uses	<ul><li>Closures</li><li>Consumer Applications</li><li>Cosmetic Packaging</li><li>Food Containers</li><li>Food Packaging</li></ul>	<ul><li>Food Service Applications</li><li>Gaskets</li><li>Handles</li><li>Kitchenware</li><li>Lids</li></ul>	<ul><li>Non-specific Food Applications</li><li>Rubber Replacement</li><li>Toothbrush Handles</li><li>Toys</li></ul>
Agency Ratings	<ul> <li>EU Food Contact, Unspecified Rating</li> </ul>	FDA Food Contact, Unspecificating	ed
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>		
Appearance	Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density	1.05	g/cm³	ISO 1183	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress (100% Strain)	189	psi	ISO 37	
Tensile Stress (300% Strain)	377	psi	ISO 37	
Tensile Strength (Break)	1120	psi	ISO 37	
Tensile Elongation (Break)	800	%	ISO 37	
Compression Set <sup>2</sup>			ISO 815	
73°F, 22 hr	23	%		
158°F, 22 hr	43	%		
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 5 sec)	50		ISO 868	
Fill Analysis	Nominal Value	Unit	Test Method	

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

109 Pa·s

Revision Date: 6/1/2016

ISO 11443

## Monprene® RG-17250 (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

Processing Information				
njection	Nominal Value	Unit		
Rear Temperature	248 to 320	°F		
Middle Temperature	320 to 446	°F		
Front Temperature	356 to 446	°F		
Nozzle Temperature	356 to 446	°F		
Processing (Melt) Temp	356 to 446	°F		
Mold Temperature	59 to 122	°F		
Injection Rate	Fast			
Back Pressure	72.5 to 218	psi		
Screw Speed	50 to 100	rpm		
Cushion	0.118 to 0.787	in		

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

#### **Extrusion Notes**

Screw Speed: 30 to 100 rpm

## **Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

#### **Teknor Apex Company** Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Pawtucket, Rhode Island 02861 U.S.

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com



Revision Date: 6/1/2016

<sup>&</sup>lt;sup>2</sup> Method B