

Sarlink® TPV X11044DB

Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, June 29, 2017

General Information

Product Description

SARLINK® TPV 11000 series are engineered low friction slip coating materials designed primarily for demanding automotive and industrial applications. SARLINK® TPV X11044DB is a high hardness, low density grade with good UV resistance and superior abrasion resistance and can be co-extruded with TPE-S, TPE-V, and EPDM.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Bondability • Chemical Resistant • Good Adhesion • Good Processability	• High Hardness • High Heat Resistance • Low Compression Set • Low Density	• Low Friction • Low Specific Gravity • Specialty Grade • UV Resistant
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Window Encapsulation	• Coating Applications • Industrial Applications • Rubber Replacement	• Weatherstripping
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• DAIMLER DBL 5578 Color: Black • NISSAN Unspecified Color: Black	• VAG VW501 23 Color: Black • VAG VW501 2G Color: Black	
Appearance	• Black	• Opaque	
Forms	• Pellets		
Processing Method	• Coextrusion	• Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density			
--	0.960	g/cm ³	ISO 1183
--	0.960	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus			
--	25100	psi	ISO 178
--	25100	psi	ASTM D790
Coefficient of Friction (vs. Glass - Dynamic)	0.25		ASTM D1894
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength - Across Flow			
Break	1600	psi	ISO 37
Break	1600	psi	ASTM D412
Tensile Elongation - Across Flow			
Break	550	%	ISO 37
Break	550	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			
Shore D, 5 sec, Injection Molded	40		ISO 868
Shore D, 5 sec, Injection Molded	40		ASTM D2240

上海松塑塑化科技有限公司
 TEKNOR APEX 特诺尔爱佩斯 一级分销商
 teknorapex.shshs.com 联系电话: 021-58958888

Revision Date: 10/13/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV X11044DB

Teknor Apex Company - Thermoplastic Vulcanizate

Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity			
392°F, 206 sec ⁻¹	312	Pa·s	ISO 11443
392°F, 206 sec ⁻¹	312	Pa·s	ASTM D3835

Additional Information

Co-extrudes with good adhesion to TPE-S;
 Co-extrudes with good adhesion to TPV;
 Co-extrudes with good adhesion to EPDM

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	350 to 410	°F
Cylinder Zone 2 Temp.	360 to 420	°F
Cylinder Zone 3 Temp.	380 to 440	°F
Cylinder Zone 4 Temp.	380 to 440	°F
Cylinder Zone 5 Temp.	380 to 440	°F
Die Temperature	380 to 440	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
 Fax: 401-725-8095
 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
 Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 10/13/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.