

Sarlink® TPE RV-2670D

Teknor Apex Company - Thermoplastic Elastomer

Friday, June 30, 2017

General Information

Product Description

Sarlink RV-2670D is a high performance thermoplastic elastomer, available in NAT and BLK, used in a variety of transportation applications. Sarlink RV-2670D is a high hardness, high density, filled grade with a 400k psi modulus that is UV stabilized and suitable for extrusion and injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Toughness • High Density	• High Hardness • High Specific Gravity • Light Stabilized • Low Flow • Lubricated	• Slip • Sunlight Resistant • UV Resistant • Weather Resistant
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Exterior Trim • Racks	
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	390000	psi	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	1850	psi	
Flow : 100% Strain	2500	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	2590	psi	
Flow : Break	3160	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	120	%	
Flow : Break	140	%	
Tear Strength ³			ISO 34-1
Across Flow	1000	lbf/in	
Flow	710	lbf/in	
Compression Set ⁴			ISO 815
73°F, 22 hr	67	%	
158°F, 22 hr	94	%	
194°F, 70 hr	93	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D, 1 sec, Injection Molded	70		
Shore D, 5 sec, Injection Molded	69		
Shore D, 15 sec, Injection Molded	68		

上海松翰塑化科技有限公司
 TEKNOR APEX 特纳尔爱佩斯 一级分销商
 teknorapex.sh.cn 联系电话: 021-58958519

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE RV-2670D

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	6.1	%	
Flow : 230°F, 1008 hr	11	%	
Across Flow : 100% Strain 230°F, 1008 hr	16	%	
Flow : 100% Strain 230°F, 1008 hr	29	%	
Across Flow : 257°F, 168 hr	3.9	%	
Flow : 257°F, 168 hr	7.9	%	
Across Flow : 100% Strain 257°F, 168 hr	20	%	
Flow : 100% Strain 257°F, 168 hr	33	%	
Change in Tensile Strain at Break in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	-31	%	
Flow : 230°F, 1008 hr	-18	%	
Across Flow : 257°F, 168 hr	16	%	
Flow : 257°F, 168 hr	9.2	%	
Change in Shore Hardness in Air			ISO 188
Shore D, 230°F, 1008 hr ⁶	0.60		
Shore D, 230°F, 1008 hr ⁷	1.2		
Shore D, 230°F, 1008 hr ⁸	1.4		
Shore D, 257°F, 168 hr ⁸	0.10		
Shore D, 257°F, 168 hr ⁷	1.1		
Shore D, 257°F, 168 hr ⁶	1.3		

Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	613	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	380 to 450	°F
Middle Temperature	380 to 450	°F
Front Temperature	380 to 450	°F
Nozzle Temperature	380 to 450	°F
Processing (Melt) Temp	380 to 450	°F
Mold Temperature	60 to 110	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 430	°F
Cylinder Zone 2 Temp.	380 to 430	°F
Cylinder Zone 3 Temp.	380 to 430	°F



Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE RV-2670D

Teknor Apex Company - Thermoplastic Elastomer

Extrusion	Nominal Value	Unit
Cylinder Zone 4 Temp.	380 to 430	°F
Cylinder Zone 5 Temp.	380 to 430	°F
Die Temperature	380 to 430	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ Type 1

⁶ 1 sec

⁷ 5 sec

⁸ 15 sec

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*

505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100

Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

info@teknorapex.com

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.