

Sarlink® TPE ML-1170B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Thursday, June 29, 2017

General Information

Product Description


Sarlink ML-1100 is a general purpose thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1170B BLK is a medium hardness, high density, filled grade suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Filled • Good Moldability • Good Processability	• High Density • High Specific Gravity • Medium Flow	• Medium Hardness
Uses	• Automotive Applications • Automotive Interior Parts	• General Purpose • Grommets	
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	293	psi	
Flow : 100% Strain	403	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	856	psi	
Flow : Break	798	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	780	%	
Flow : Break	680	%	
Tear Strength ³			ISO 34-1
Across Flow	150	lbf/in	
Flow	150	lbf/in	
Compression Set ⁴			ISO 815
73°F, 22 hr	35	%	
158°F, 22 hr	53	%	
194°F, 70 hr	77	%	
257°F, 70 hr	94	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	74		
Shore A, 5 sec, Injection Molded	72		
Shore A, 15 sec, Injection Molded	70		



Revision Date: 2/24/2017

Sarlink® TPE ML-1170B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer


Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	4.7	%	
Flow : 230°F, 1008 hr	-2.2	%	
Across Flow : 100% Strain 230°F, 1008 hr	9.6	%	
Flow : 100% Strain 230°F, 1008 hr	8.9	%	
Across Flow : 257°F, 168 hr	2.4	%	
Flow : 257°F, 168 hr	-8.3	%	
Across Flow : 100% Strain 257°F, 168 hr	10	%	
Flow : 100% Strain 257°F, 168 hr	13	%	
Change in Tensile Strain at Break in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	4.9	%	
Flow : 230°F, 1008 hr	-0.10	%	
Across Flow : 257°F, 168 hr	6.8	%	
Flow : 257°F, 168 hr	0.40	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr ⁶	2.0		
Shore A, 230°F, 1008 hr ⁷	3.1		
Shore A, 230°F, 1008 hr ⁸	3.6		
Shore A, 257°F, 168 hr ⁶	2.4		
Shore A, 257°F, 168 hr ⁷	4.1		
Shore A, 257°F, 168 hr ⁸	4.8		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	138	Pa·s	ASTM D3835
Additional Information	Nominal Value	Unit	Test Method
Xenon Weatherometer			SAE J1885
Delta E - 1250 kJ	0.140		
Delta E - 2500 kJ	0.600		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).



Revision Date: 2/24/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE ML-1170B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ Type 1

⁶ 1 sec

⁷ 5 sec

⁸ 15 sec

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 2/24/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.