

Sarlink® TPE ME-2275B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Thursday, June 29, 2017

General Information

Product Description

The Sarlink ME-2200 Series is a general purpose thermoplastic elastomer series, available in BLK, designed for automotive exterior molded applications. Sarlink ME-2275B is a medium hardness, low density, UV stabilized grade suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Adhesion • Good Processability • Light Stabilized	• Low Density • Low Flow • Low Specific Gravity • Lubricated	• Medium Hardness • Sunlight Resistant • UV Resistant
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Exterior Trim • Rubber Replacement	
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.926	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	360	psi	
Flow : 100% Strain	473	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	1650	psi	
Flow : Break	1020	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	840	%	
Flow : Break	650	%	
Tear Strength ³			ISO 34-1
Across Flow	180	lbf/in	
Flow	210	lbf/in	
Compression Set ⁴			ISO 815
73°F, 22 hr	23	%	
158°F, 22 hr	42	%	
194°F, 70 hr	64	%	
257°F, 70 hr	86	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	77		
Shore A, 5 sec, Injection Molded	74		
Shore A, 15 sec, Injection Molded	72		



Revision Date: 10/28/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPE ME-2275B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	4.4	%	
Flow : 230°F, 1008 hr	4.3	%	
Across Flow : 100% Strain 230°F, 1008 hr	8.5	%	
Flow : 100% Strain 230°F, 1008 hr	13	%	
Across Flow : 257°F, 168 hr	3.5	%	
Flow : 257°F, 168 hr	1.4	%	
Across Flow : 100% Strain 257°F, 168 hr	6.5	%	
Flow : 100% Strain 257°F, 168 hr	13	%	
Change in Tensile Strain at Break in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	0.40	%	
Flow : 230°F, 1008 hr	-1.9	%	
Across Flow : 257°F, 168 hr	0.80	%	
Flow : 257°F, 168 hr	-3.4	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr ⁶	1.8		
Shore A, 230°F, 1008 hr ⁷	1.5		
Shore A, 230°F, 1008 hr ⁸	2.2		
Shore A, 257°F, 168 hr ⁷	0.30		
Shore A, 257°F, 168 hr ⁶	0.60		
Shore A, 257°F, 168 hr ⁸	0.90		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	203	Pa·s	ASTM D3835
Additional Information	Nominal Value	Unit	Test Method
Xenon Weatherometer			SAE J2527
Delta E - 1250 kJ	0.500		
Delta E - 2500 kJ	0.330		

Legal Statement


The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	390 to 410	°F
Middle Temperature	400 to 420	°F
Front Temperature	410 to 430	°F
Nozzle Temperature	420 to 440	°F
Processing (Melt) Temp	420 to 440	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in

Revision Date: 10/28/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.



Sarlink® TPE ME-2275B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ Type 1

⁶ 5 sec

⁷ 1 sec

⁸ 15 sec

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100
Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk

上海松翰塑化科技有限公司
TEKNOR APEX 特诺尔爱佩斯 一级分销商
teknorapex.shshsj.com 联系电话: 021-58958519

Revision Date: 10/28/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.