

Chemlon® 100 HU

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday June 30 2017

	General l	Information			
General					
Material Status	Commercial: Active				
Availability	Asia Pacific	• Europe	North America		
Additive	Heat Stabilizer	 Lubricant 	UV Stabilizer		
Features	General PurposeGood ProcessabilityGood Toughness	Heat StabilizedHigh StrengthLubricated	UV Resistant		
Uses	 Appliances 	 Automotive Applications 	 Electrical/Electronic Application 		
Appearance	• Grey				
Forms	• Pellets				
Processing Method	Injection Molding				
	ASTM & IS	O Properties ¹			
Physical		Nominal Value Unit	Test Method		

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.14		ASTM D792	
Molding Shrinkage - Flow	0.015	in/in	ASTM D955	
Water Absorption (24 hr)	1.2	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	12000	psi	ASTM D638	
Tensile Elongation (Break)	25	%	ASTM D638	
Flexural Modulus	425000	psi	ASTM D790	
Flexural Strength	16500	psi	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (73°F)	1.0	ft·lb/in	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
264 psi, Unannealed	190	°F		
Melting Temperature	490	°F		
Flammability	Nominal Value	Unit	Test Method	
Flame Rating	V-2		UL 94	

Processing Information			
Injection	Nominal Value Unit		
Drying Temperature	150 to 180 °F		
Suggested Max Moisture	0.20 %		
Rear Temperature	540 °F		
Middle Temperature	520 °F		
Front Temperature	500 °F		
Nozzle Temperature	500 F 上 10 10 10 10 10 10 10 10 10 10 10 10 10		
Mold Temperature	70 to 200 PH 19 1958519		
Injection Pressure	5000 to 20000 psi		
Screw Speed	60 to 720 ripin		
Notes	500 °F		
1 Typical properties: these are not to be construed as specifications	13		

Revision Date: 12/11/2008

¹ Typical properties: these are not to be construed as specifications.

Chemlon® 100 HU

Teknor Apex Company (Chem Polymer) - Polyamide 66

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/11/2008