

Chemlon® 100 XH

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

General Information				
externally lubricated for excellent feed	and mold release properties.			
Commercial: Active				
Asia Pacific	• Europe	North America		
 Heat Stabilizer 	Lubricant			
General Purpose	Good Toughness	High Strength		
 Good Processability 	 Heat Stabilized 	 Lubricated 		
 Appliances 	 Automotive Applications 	 Electrical/Electronic Applications 		
Black	Natural Color			
• Pellets				
Injection Molding				
	Commercial: Active Asia Pacific Heat Stabilizer General Purpose Good Processability Appliances Black Pellets	externally lubricated for excellent feed and mold release properties. Commercial: Active Asia Pacific Europe Heat Stabilizer General Purpose Good Toughness Heat Stabilized Appliances Automotive Applications Black Pellets		

ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	12000	psi	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	425000	psi	ASTM D790
Flexural Strength	16500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.0	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	190	°F	
Melting Temperature	490	°F	
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94

Processing Information			
Injection	Nominal Value Unit		
Drying Temperature	150 to 180 °F		
Suggested Max Moisture	0.20 %		
Rear Temperature	540 °F		
Middle Temperature	520 °F		
Front Temperature	500 °F		
Nozzle Temperature	500 °F		
Mold Temperature	500 °F 70 to 200 °F 10 to 200 °F		
Injection Pressure	5000 to 20000 psi		
Screw Speed	50 60 20 pp		
Notes	NOR shehei.com		
¹ Typical properties: these are not to be construed as specifications.	500 °F 70 to 200 °F 5000 to 20000 pai 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1		

Notes

Revision Date: 12/11/2008

¹ Typical properties: these are not to be construed as specifications.

Chemlon® 100 XH

Teknor Apex Company (Chem Polymer) - Polyamide 66

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/11/2008