

Chemion® 133 GHL

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

General Information					
Product Description					
Chemlon 133 GHL contains extra	a lubrication, this is denoted by the "L" ir	n the grade designation.			
General					
Material Status	Commercial: Active				
Availability	Asia Pacific	• Europe	North America		
Filler / Reinforcement	Glass Fiber, 33% Filler by Weight				
Additive	Heat Stabilizer	 Lubricant 			
Features	Good ProcessabilityGood Toughness	Heat StabilizedHigh Strength	Lubricated		
Appearance	Black				
Forms	 Pellets 				
Processing Method	Injection Molding				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.38		ASTM D792	
Molding Shrinkage - Flow	3.0E-3	in/in	ASTM D955	
Water Absorption (24 hr)	0.70	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	25500	psi	ASTM D638	
Tensile Elongation (Break)	2.0	%	ASTM D638	
Flexural Modulus	1.20E+6	psi	ASTM D790	
Flexural Strength	35000	psi	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (73°F)	2.0	ft·lb/in	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
264 psi, Unannealed	480	°F		
Melting Temperature	490	°F		
Flammability	Nominal Value	Unit	Test Method	
Flame Rating	НВ		UL 94	

Processing Information			
Injection	Nominal Value Unit		
Drying Temperature	150 to 180 °F		
Suggested Max Moisture	0.20 %		
Rear Temperature	560 °F		
Middle Temperature	540 °F		
Front Temperature	530 下土		
Nozzle Temperature	530 Feb 1 18 18 18 19 19 19 19 19 19 19 19 19 19 19 19 19		
Mold Temperature	140 to 200 °F/1 021-3		
Injection Pressure	5000 to 20000, psi		
Screw Speed	530 年 530 年 530 年 530 年 530 60 年 5000 jo 20000 nosi TEKNOR 60 fo 120 rpm		
Notes	\		

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 12/11/2008

Chemlon® 133 GHL Teknor Apex Company (Chem Polymer) - Polyamide 66

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue

Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/11/2008