TEKNOR APEX

## Chemlon<sup>®</sup> 125-15 MGHU

Teknor Apex Company (Chem Polymer) - Polyamide 66

Friday, June 30, 2017

General			
Material Status	Commercial: Active		
Availability	Asia Pacific	Europe	North America
Filler / Reinforcement	<ul> <li>Glass Fiber, 15% Filler by Weight</li> </ul>	Mineral, 25% Filler by Weight	
Additive	Heat Stabilizer	UV Stabilizer	
Features	<ul><li>Good Dimensional Stability</li><li>Good Processability</li><li>Good Toughness</li></ul>	<ul><li>Heat Stabilized</li><li>High Rigidity</li><li>High Strength</li></ul>	<ul><li>Low Warpage</li><li>UV Resistant</li></ul>
Appearance	Black	Natural Color	
Forms	Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.42		ASTM D792	
Molding Shrinkage - Flow	5.0E-3	in/in	ASTM D955	
Water Absorption (24 hr)	0.70	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	17000	psi	ASTM D638	
Tensile Elongation (Break)	2.0	%	ASTM D638	
Flexural Modulus	1.05E+6	psi	ASTM D790	
Flexural Strength	26500	psi	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (73°F)	1.1	ft·lb/in	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
264 psi, Unannealed	473	°F		
Melting Temperature	490	°F		

Processing Information				
Nominal Value Unit				
150 to 180 °F				
0.20 %				
560 °F				
540 °F				
530 °F				
530 °F				
140 to 200 °F				
5000 to 20000 psite 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1				
60.161 120 rpm = M.M. 021-58950				
LA APEX FOR BERE				
TEKNOrapex.sh5				
	Nominal Value         Unit           150 to 180         °F           0.20         %           560         °F           540         °F           530         °F			

Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

## Chemlon® 125-15 MGHU Teknor Apex Company (Chem Polymer) - Polyamide 66

## Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864

info@teknorapex.com

Teknor Apex U.K. Ltd.

Tat Bank Road Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100 Fax: (44) 121-544-5530

etpsales@teknorapex.co.uk



Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.